

## LGEM 2

# SKF High Viscosity Bearing Grease with Solid Lubricants

SKF LGEM 2 is a high viscosity, mineral oil based grease using a lithium soap. Its content of molybdenum disulphide and graphite provides extra protection for harsh applications subjected to high loads, heavy vibrations and slow rotations.

- High oxidation stability
- Molybdenum disulphide and graphite provide lubrication even if the oil film breaks down

### Typical applications:

- Rolling element bearings running at low speed and very high loads
- Jaw crushers
- Track laying machines
- Lift mast wheels
- Building machines such as mechanical rams, crane arms and crane hooks



## Technical data

### Designation **LGEM 2/(pack size)**

DIN 51825 code	KPF2K-20
NLGI consistency class	2
Soap type	Lithium
Colour	Black
Base oil type	Mineral
Operating temperature range	-20 to +120 °C (-5 to +250 °F)
Dropping point DIN ISO 2176	>180 °C (>355 °F)
Base oil viscosity	
40 °C, mm <sup>2</sup> /s	500
100 °C, mm <sup>2</sup> /s	32
Penetration DIN ISO 2137	
60 strokes, 10 <sup>-1</sup> mm	265–295
100 000 strokes, 10 <sup>-1</sup> mm	325 max.
Mechanical stability	
Roll stability, 50 hrs at 80 °C, 10 <sup>-1</sup> mm	345 max.
V2F test	'M'

### Corrosion protection

Emcor: – standard ISO 11007	0–0
– water washout test	0–0

### Water resistance

DIN 51 807/1, 3 hrs at 90 °C	1 max.
---------------------------------	--------

### Oil separation

DIN 51 817, 7 days at 40 °C, static, %	1–5
---	-----

### Lubrication ability

R2F, running test B at 120 °C	Pass at 100 °C (210 °F)
-------------------------------	-------------------------

### Copper corrosion

DIN 51 811, 110 °C	2 max.
--------------------	--------

### EP performance

Wear scar DIN 51350/5, 1 400 N, mm	1,4 max.
4–ball test, welding load DIN 51350/4, N	3 000 min.

### Available pack sizes

420 ml cartridge
5, 18, 180 kg
SKF SYSTEM 24 (LAGD/TLSD)



### SKF lubricants offer major competitive advantages:

- Designed and tested to outperform under real conditions
- Product data include specific test results enabling a better selection
- Strict quality control of every production batch help ensure consistent performance
- Quality control allows SKF to offer a five-year shelf-life\* from the date of production



Production processes and raw materials vastly influence grease properties and performance. It is virtually impossible to select or compare greases based only on their composition. Therefore, performance tests are needed to provide crucial information. In over 100 years, SKF has accrued vast knowledge about the interaction of lubricants, materials and surfaces.



This knowledge has led SKF, in many cases, to set industry standards in bearing lubricant testing. Emcor, ROF, ROF+, V2F, R2F and Bequiet are just some of the multiple tests developed by SKF to assess the performance of lubricants under bearing operating conditions. Many of them are widely used by lubricant manufacturers worldwide.

\* SKF LGFP 2 food grade grease offers a two-year shelf-life from the date of production

© SKF is a registered trademark of the SKF Group.

© SKF Group 2014

The contents of this publication are the copyright of the publisher and may not be reproduced (even extracts) unless prior written permission is granted. Every care has been taken to ensure the accuracy of the information contained in this publication but no liability can be accepted for any loss or damage whether direct, indirect or consequential arising out of the use of the information contained herein.

PUB MP/P8 12044 EN · January 2014

